



## Technical Data Sheet

<b>MATERIAL:</b>	Poly(vinyl alcohol), 96% hydrolyzed	
<b>CATALOG NUMBER:</b>	351	
<b>CAS NUMBER:</b>	25213-24-5	
<b>DESCRIPTION:</b>	Highly hydrolyzed poly(vinyl alcohol)	
<b>FORMULA:</b>	$(C_4H_6O_2 \cdot C_2H_4O)_x$	
<b>TYPICAL PROPERTIES:</b>	Appearance:	Granular
	Approx Mw:	95,000
	Viscosity:	29 cp (4% aqueous solution @ 20°C)
	Refractive index:	$n_D^{20}$ 1.50
	Density:	1.29
	Melting point:	200°C
	pH:	5-7
	Solubility:	Glycerol (hot), glycols (hot), water
<b>GENERAL INFORMATION:</b>	Prepared by polymerizing vinyl acetate and hydrolyzing the resulting polymer. Highly hydrolyzed grades of poly(vinyl alcohol) exhibit increased water resistance, tensile strength, solvent resistance and adhesion to hydrophilic surfaces over partially hydrolyzed grades. Highly hydrolyzed grades of poly(vinyl alcohol) find use in quick-setting, water-resistant adhesives.	
<b>STRUCTURE:</b>		