



Technical Data Sheet

| | | | | | | | | | | | | | | | | | |
|-----------------------------|--|-------------|----------|------------|---------|------------|------------------------------------|-------------------|-----------------|----------|------|----------------|-------|-----|-----|-------------|--------------------------------------|
| MATERIAL: | Poly(vinyl alcohol), 98% hydrolyzed | | | | | | | | | | | | | | | | |
| CATALOG NUMBER: | 363 | | | | | | | | | | | | | | | | |
| CAS NUMBER: | 9002-89-5 | | | | | | | | | | | | | | | | |
| DESCRIPTION: | Fully hydrolyzed poly(vinyl alcohol) | | | | | | | | | | | | | | | | |
| FORMULA: | $(C_2H_4O)_x$ | | | | | | | | | | | | | | | | |
| TYPICAL PROPERTIES: | <table><tr><td>Appearance:</td><td>Granular</td></tr><tr><td>Approx Mw:</td><td>126,000</td></tr><tr><td>Viscosity:</td><td>60 cp (4% aqueous solution @ 20°C)</td></tr><tr><td>Refractive index:</td><td>n_D^{20} 1.50</td></tr><tr><td>Density:</td><td>1.29</td></tr><tr><td>Melting point:</td><td>200°C</td></tr><tr><td>pH:</td><td>6-8</td></tr><tr><td>Solubility:</td><td>Glycerol (hot), glycols (hot), water</td></tr></table> | Appearance: | Granular | Approx Mw: | 126,000 | Viscosity: | 60 cp (4% aqueous solution @ 20°C) | Refractive index: | n_D^{20} 1.50 | Density: | 1.29 | Melting point: | 200°C | pH: | 6-8 | Solubility: | Glycerol (hot), glycols (hot), water |
| Appearance: | Granular | | | | | | | | | | | | | | | | |
| Approx Mw: | 126,000 | | | | | | | | | | | | | | | | |
| Viscosity: | 60 cp (4% aqueous solution @ 20°C) | | | | | | | | | | | | | | | | |
| Refractive index: | n_D^{20} 1.50 | | | | | | | | | | | | | | | | |
| Density: | 1.29 | | | | | | | | | | | | | | | | |
| Melting point: | 200°C | | | | | | | | | | | | | | | | |
| pH: | 6-8 | | | | | | | | | | | | | | | | |
| Solubility: | Glycerol (hot), glycols (hot), water | | | | | | | | | | | | | | | | |
| GENERAL INFORMATION: | Prepared by polymerizing vinyl acetate and hydrolyzing the resulting polymer. Highly hydrolyzed grades of poly(vinyl alcohol) exhibit increased water resistance, tensile strength, solvent resistance and adhesion to hydrophilic surfaces over partially hydrolyzed grades. Highly hydrolyzed grades of poly(vinyl alcohol) find use in quick-setting, water-resistant adhesives. | | | | | | | | | | | | | | | | |

STRUCTURE:

Technical information and data regarding the composition, properties or use of the products described herein is believed reliable. However, no representation or warranty is made with respect thereto except as made by Sp² in writing at time of sale. Sp² cannot assume responsibility for any patent liability which may arise from the use of any product in a process, manner or formula not designed by Sp².