



Technical Data Sheet

MATERIAL:	Polyamide resin												
CATALOG NUMBER:	385												
CAS NUMBER:	68650-48-6												
DESCRIPTION:	Dimer acid based polyamide resin.												
FORMULA:	Unspecified												
TYPICAL PROPERTIES:	<table><tr><td>Appearance:</td><td>Pellets</td></tr><tr><td>Melting point:</td><td>95°C</td></tr><tr><td>Viscosity:</td><td>45 p (210°C)</td></tr><tr><td>Density:</td><td>0.97 (23°C)</td></tr><tr><td>Flashpoint:</td><td>> 570°F</td></tr><tr><td>Solubility:</td><td>Chloroform; Insoluble in water</td></tr></table>	Appearance:	Pellets	Melting point:	95°C	Viscosity:	45 p (210°C)	Density:	0.97 (23°C)	Flashpoint:	> 570°F	Solubility:	Chloroform; Insoluble in water
Appearance:	Pellets												
Melting point:	95°C												
Viscosity:	45 p (210°C)												
Density:	0.97 (23°C)												
Flashpoint:	> 570°F												
Solubility:	Chloroform; Insoluble in water												
GENERAL INFORMATION:	Polyamide resins are generally used in adhesive applications. They have good adhesion to many substrates, including elastomers and will retain flexibility at low temperatures.												
STRUCTURE:	This product is a polyamide made from dimerized tall oil fatty acids and ethylenediamine. Tall oil is a complex mixture of linoleic, oleic and other acids. Thus, the polymer has a complex structure. A simplified structure for just the linoleic acid portion would be:												