




Technical Data Sheet

MATERIAL:	Poly(p-phenylene ether sulphone)	
CATALOG NUMBER:	391	
CAS NUMBER:	25608-63-3	
DESCRIPTION:	Polyethersulphone, alternating ether/sulphone linkage	
FORMULA:	$(C_{12}H_8O_3S)_n$	
TYPICAL PROPERTIES:	Appearance:	Pellets
	Refractive index:	n_D^{20} 1.65
	Density:	1.37
	Melt flow index:	3.9 g/10min (320°C)
	Vicat softening point:	226°C
	Solubility:	Aromatic amines, highly polar aromatics (i.e. DMSO, NMP), nitrobenzene, and certain chlorinated hydrocarbons, (i.e. chloroform, methylene chloride)

GENERAL INFORMATION: Poly(p-phenylene ether sulphone) is an amorphous thermoplastic which offers a unique combination of properties. Key properties include thermal stability, an ability to withstand loads for long periods at 180°C, retention of mechanical and electrical properties up to 210°C, and low flammability. Can be used in extrusion, injection molding, and solution coating processes. Typical applications include electrical components, automotive components, and various miscellaneous housings where a combination of chemical resistance and high temperature properties are required.

STRUCTURE:

Technical information and data regarding the composition, properties or use of the products described herein is believed reliable. However, no representation or warranty is made with respect thereto except as made by Sp² in writing at time of sale. Sp² cannot assume responsibility for any patent liability which may arise from the use of any product in a process, manner or formula not designed by Sp².