




## Technical Data Sheet

<b>MATERIAL:</b>	Poly(ethylene terephthalate)
<b>CATALOG NUMBER:</b>	418
<b>CAS NUMBER:</b>	25038-59-9
<b>DESCRIPTION:</b>	Ethyleneglycol/terephthalic acid polyester
<b>FORMULA:</b>	$(C_{10}H_8O_4)_x$

**TYPICAL PROPERTIES:**

Appearance:	Flakes
Density:	1.385
Refractive index:	$n_D^{25}$ 1.5750
Inherent viscosity:	0.7
Glass transition temp:	81°C
Melting point:	250-265°C
Solubility:	DMSO (hot), HFIP, nitrobenzene, phenol

**GENERAL INFORMATION:** Polyester prepared by the condensation of ethylene glycol and terephthalic acid. Polyethylene terephthalate has been used in a variety of applications including clothing, electrical insulation, magnetic tape, food packaging, bottles, and various photographic film applications.

**STRUCTURE:**

Technical information and data regarding the composition, properties or use of the products described herein is believed reliable. However, no representation or warranty is made with respect thereto except as made by Sp<sup>2</sup> in writing at time of sale. Sp<sup>2</sup> cannot assume responsibility for any patent liability which may arise from the use of any product in a process, manner or formula not designed by Sp<sup>2</sup>.