



Technical Data Sheet

MATERIAL:	Poly(ethylene glycol) monomethyl ether
CATALOG NUMBER:	497
CAS NUMBER:	9004-74-4
DESCRIPTION:	Mono-methoxy terminated polyethylene glycol
FORMULA:	$(C_2H_4O)_x CH_4O$


TYPICAL PROPERTIES:

Appearance:	Liquid (25°C)
Approx Mw:	550
Density:	1.106 (20°C)
Refractive index:	n_D^{20} 1.455
Viscosity:	7.5 cs (99°C)
Melting point:	20°C
Boiling point:	> 200°C (dec)
Flash point:	375°F
Solubility:	Acetone, chloroform, cyclohexanone, dichloromethane, DMF, MEK, toluene (hot), water

GENERAL INFORMATION:

Prepared by the anionic ring opening polymerization of ethylene oxide. Each chain has a methyl group at one end of the polymer chain and are, therefore, more compatible with hydrocarbons than the corresponding polyethylene glycols. In general, as the molecular weight of polyethylene glycols increases, water solubility, vapor pressure, hygroscopicity and solubility in organic solvents decrease; at the same time freezing or melting range, specific gravity, flash point, and viscosity increase. Methoxy terminated polyethylene glycols can be converted through their primary alcohol groups to monoesters, amines, acetals, and diethers. Low molecular weight polyethylene glycols are used as intermediates in chemical manufacturing (e.g. surfactants and thickeners), in pharmaceutical applications (e.g. ointments, suppositories) and in cosmetics (creams and lotions).

STRUCTURE:



Technical information and data regarding the composition, properties or use of the products described herein is believed reliable. However, no representation or warranty is made with respect thereto except as made by Sp² in writing at time of sale. Sp² cannot assume responsibility for any patent liability which may arise from the use of any product in a process, manner or formula not designed by Sp².