

6265 DEAN PARKWAY ONTARIO NY 14519 WWW.SCIPOLY.COM

Technical Data Sheet

MATERIAL: Poly(butadiene-co-acrylonitrile), dicarboxy terminated

CATALOG NUMBER: 519

CAS NUMBER: 68891-46-3

DESCRIPTION: Terpolymer of butadiene, acrylonitrile and acrylic acid, dicarboxy terminated

FORMULA: $(C_4H_6)_m(C_3H_3N)_n(COOH)_2$

TYPICAL PROPERTIES:

Appearance: Liquid
Acrylonitrile content: 26%
Carboxyl content: 2.40%

Approx Mw: 17,000 [GPC]
Brookfield viscosity: 500,000 cp (27°C)

Density: 0.960 (25°C)

Functionality: 1.85
Solubility parameter: 9.14
Glass transition temp: -39°C
Flash point: >230°F
Solubility: THF

GENERAL INFORMATION: Used in epoxy-based adhesive formulations, composites and coatings. Also

used as an intermediate in corrosion-resistant vinyl esters, acrylated epoxes

and radiation curing formulations.

STRUCTURE: