



Technical Data Sheet

MATERIAL:	Poly(tetramethylene ether) glycol																
CATALOG NUMBER:	693																
CAS NUMBER:	25190-06-1																
DESCRIPTION:	Poly(1,4-oxybutylene) glycol; Polytetrahydrofuran																
FORMULA:	$(C_4H_8O)_xH_2O$																
TYPICAL PROPERTIES:	<table><tr><td>Appearance:</td><td>Fused mass</td></tr><tr><td>Approx Mw:</td><td>1,000</td></tr><tr><td>Density:</td><td>0.98 (40°C)</td></tr><tr><td>Hydroxyl number:</td><td>111.2</td></tr><tr><td>Boiling point:</td><td>> 204°C</td></tr><tr><td>Melting point:</td><td>19°C</td></tr><tr><td>Flash point:</td><td>380°F</td></tr><tr><td>Solubility:</td><td>Alcohol; slightly in water; insoluble in ether</td></tr></table>	Appearance:	Fused mass	Approx Mw:	1,000	Density:	0.98 (40°C)	Hydroxyl number:	111.2	Boiling point:	> 204°C	Melting point:	19°C	Flash point:	380°F	Solubility:	Alcohol; slightly in water; insoluble in ether
Appearance:	Fused mass																
Approx Mw:	1,000																
Density:	0.98 (40°C)																
Hydroxyl number:	111.2																
Boiling point:	> 204°C																
Melting point:	19°C																
Flash point:	380°F																
Solubility:	Alcohol; slightly in water; insoluble in ether																
GENERAL INFORMATION:	This polymer finds application as the flexible segment in urethane elastomers, fibers, coatings and adhesives and is also of interest in polyester modification.																
STRUCTURE:																	