



## Technical Data Sheet

<b>MATERIAL:</b>	Ethylene/vinyl acetate copolymer														
<b>CATALOG NUMBER:</b>	784														
<b>CAS NUMBER:</b>	24937-78-8														
<b>DESCRIPTION:</b>	Random copolymer of ethylene and vinyl acetate														
<b>FORMULA:</b>	$(C_4H_6O_2.C_2H_4)_x$														
<b>TYPICAL PROPERTIES:</b>	<table><tr><td>Appearance:</td><td>Beads</td></tr><tr><td>Vinyl acetate content:</td><td>45 wt%</td></tr><tr><td>Approx Mw:</td><td>250,000 [GPC]</td></tr><tr><td>Melt flow index:</td><td>2-5 g/10min</td></tr><tr><td>Density:</td><td>0.98 (23°C)</td></tr><tr><td>Softening point(R&amp;B):</td><td>182°C</td></tr><tr><td>Solubility:</td><td>Benzene, dioxane, MEK, methylene chloride, THF, toluene, xylene</td></tr></table>	Appearance:	Beads	Vinyl acetate content:	45 wt%	Approx Mw:	250,000 [GPC]	Melt flow index:	2-5 g/10min	Density:	0.98 (23°C)	Softening point(R&B):	182°C	Solubility:	Benzene, dioxane, MEK, methylene chloride, THF, toluene, xylene
Appearance:	Beads														
Vinyl acetate content:	45 wt%														
Approx Mw:	250,000 [GPC]														
Melt flow index:	2-5 g/10min														
Density:	0.98 (23°C)														
Softening point(R&B):	182°C														
Solubility:	Benzene, dioxane, MEK, methylene chloride, THF, toluene, xylene														
<b>GENERAL INFORMATION:</b>	High vinyl acetate content EVA copolymers are typically used in peroxide cured rubber articles to impart improved heat, ozone, weathering, and oil resistance. Typical applications include molded and extruded goods, cable jackets, proofed goods and cellular rubber products.														
<b>STRUCTURE:</b>															

Technical information and data regarding the composition, properties or use of the products described herein is believed reliable. However, no representation or warranty is made with respect thereto except as made by Sp<sup>2</sup> in writing at time of sale. Sp<sup>2</sup> cannot assume responsibility for any patent liability which may arise from the use of any product in a process, manner or formula not designed by Sp<sup>2</sup>.